

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
24 June 2004 (24.06.2004)

PCT

(10) International Publication Number
WO 2004/053020 A1

(51) International Patent Classification⁷: **C09K 19/46,**
19/02

(21) International Application Number:
PCT/EP2003/012952

(22) International Filing Date:
19 November 2003 (19.11.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
02027739.8 11 December 2002 (11.12.2002) EP

(71) Applicant (for all designated States except US): **MERCK
PATENT GMBH** [DE/DE]; Frankfurter Strasse 250,
64293 Darmstadt (DE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **FRANCIS,
Matthew** [GB/GB]; 21 Stratford Place, Eastleigh SO50
4NB (GB). **GOULDING, Mark, John** [GB/GB]; 50

Seymour Road, Ringwood, Hampshire BH24 1SH (GB).
JONES, John, Clifford [GB/GB]; The Old Granary
Crowcroft, Leighsinton WR13 5ED (GB). **BELDON,**
Steve [GB/GB]; Bridge Street 35, Ledbury Herefordshire
HR8 2AH (GB).

(74) Common Representative: **MERCK PATENT GMBH;**
Frankfurter Strasse 250, 64293 Darmstadt (DE).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC,
SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA,
UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (BW, GH,
GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,

[Continued on next page]

(54) Title: FAST SWITCHING LIQUID CRYSTAL COMPOSITIONS FOR USE IN BISTABLE LIQUID CRYSTAL DEVICES





Illustration of zenithal bistability using grating alignment
(with the lines indicating the local director) showing a) the high tilt
(continuous) and b) the low tilt (defect) states.



The a) VAN and b) TN geometries for ZBD showing the
director distribution of the high and low tilt states.

(57) Abstract: The invention is directed to the use of a fast switching liquid crystal composition said composition comprising at least 30 weight% of a component (α) containing one or more compounds having a dielectric anisotropy $\Delta\epsilon$ of at least 25, whereby at least 25 weight% of said compounds have a dielectric anisotropy $\Delta\epsilon$ of at least 40; and at least 5 weight% of a component (δ) containing one or more compounds having a ratio of γ_1/T_{NI}^K of 0.51 mPa-s/K or less, a clearing point T_{NI} of at least 100°C and a rotational viscosity γ_1 of not more than 190 mPa-s (wherein γ_1 is the rotational viscosity at 20 °C in mPa-s and T_{NI}^K is the clearing point in degrees Kelvin); in a bistable liquid crystal device and especially in a zenithal bistable nematic liquid crystal device, a nematic liquid crystal medium, and a bistable liquid crystal device comprising said fast switching liquid crystal composition.



ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE,
SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA,
GN, GQ, GW, ML, MR, NE, SN, TD, TG).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

Published:

— *with international search report*